

Features & Benefits

Two-component silicone potting, 1 to 1, curing at room temperature.

- REACH, ROHS, UL VO certified
- Good waterproof
- Good thermal conductivity
- Easy to mix and use

Application

- Power moduls
- Adaptors
- Transformers
- Ballasts
- Sensors
- Electric control units product

Description

Tensan silicone 1 to 1 encapsulants are supplied as two part liquid component kits. After mixing, two parts silicone will be cured as a flexible elastomer, which is well used for the protection of electrical and PCB system assemble application. The duration of application and the curing time at room temperature are independent of the number of materials.

Packing Information

20KG/25KG/BUCKET
24 BUCKET/PALLET

Storage and Validity

Stored in room temperature, and in a cool, ventilated, dry place.
Shelf life: 6 month

Typical Properties

Item	Index
Color	Part A: White / light gray Part B: White
Viscosity mPa·s (25°C)	Part A: 3500 Part B: 3200
Specific Gravity (Cured)	1.70
Mix Ratio	1:1
Viscosity mPa·s (25°C)	3400
Density g/cm ³ (25°C)	1.70±0.05
Working Time at 25°C (minutes)	60
Heat Cure Time Hr/°C	0.5/80
Hardness (Shore A)	50
Thermal Conductivity (W/mK)	0.8
Dielectric Constant (1MHz 25°C)	3.0
Dielectric Strength kV/mm (25°C)	24
Volume Resistivity (DC500V) Ω·cm	1.5×10 ⁻¹⁵
UL 94 Flame Classification	94 V-0

How Can We Help You Today

Tell us about your performance, design, and manufacturing challenges. Let us put our silicone-based materials, expertise, application knowledge, and processing experience to work for you.

For more about our product, please visit:
www.sztensan.com