Colour Fastness To Washing

(ISO 105-C06:2010; Test No.:Ref.A2S, Machine wash at 30℃ with 4g/L ECE (B) and 1g/L Sodium Perborate with 10 Steel Balls)

-	Unit	(A)
Change in Shade	-	4-5
Staining On Multi-fibre Stripe		
Acetate	-	4-5
Cotton	-	4-5
Polyamide	-	4-5
Polyester	-	4-5
Acrylic	-	4-5
Wool	-	4-5

Remark: Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is worst and 5 is best.

Pilling Resistance

(ISO 12945-1:2000; 18000 Revolutions (5 Hours), testing in ICI Pilling Tester.)

As Received

-	Unit	(A)
Pilling Rating	-	4-5

Remarks: Pilling Rating
5 No change
4 Slight surface fuzzing and/or partially formed pills
3 Moderate surface fuzzing and/or moderate pilling. Pills of varying size and density partially covering the specimen surface.
2 Distinct surface fuzzing and/or distinct pilling. Pills of varying size and density covering a large proportion of the specimen surface.
1 Dense surface fuzzing and/or severe pilling. Pills of varying size and density covering the whole of the specimen surface.

End of Report

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms-and-conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/terms-and-conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing, inspection reports & certificates, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
| Building, No.889 Yishan Road, Xuhui District, Shanghai, China 200233 | t (86-21) 61402666 | f (86-21) 64881763 | www.sgsgroup.com.cn
中国·上海·徐汇区宜山路889号3号楼 邮编: 200233 | t (86-21) 61402555 | f (86-21) 64881763 | e sgs.china@sgs.com
Member of the SGS Group (SGS SA)